



**UNIVERSITI PUTRA MALAYSIA**

**SYNTHESIS OF PALM-BASED  
TRIMETHYLOLPROPANE ESTERS AND THEIR  
POTENTIAL USE AS LUBRICANT BASESTOCK**

**ROBI' AH BINTI YUNUS**

**FK 2003 51**

**SYNTHESIS OF PALM-BASED  
TRIMETHYLOLPROPANE ESTERS AND THEIR  
POTENTIAL USE AS LUBRICANT BASESTOCK**

**By**

**ROBI'AH BINTI YUNUS**

**Thesis Submitted to the School of Graduate Studies,  
Universiti Putra Malaysia in Fulfilment of the  
Requirement for the Degree of Doctor of Philosophy**

**October 2003**



**DEDICATED TO**

**ABANG, AMMIL, AA, YAYA, AINA, MA AND BAPA**

Abstract of thesis presented to the Senate of Universiti Putra Malaysia in fulfilment of the requirement for the degree of Doctor of Philosophy

**SYNTHESIS OF PALM-BASED TRIMETHYLOLPROPANE ESTERS  
AND THEIR POTENTIAL USE AS LUBRICANT BASESTOCK**

**By**

**ROBI'AH BINTI YUNUS**

**October 2003**

**Chairman: Associate Professor Fakhru'l-Razi Ahmadun, Ph.D.**

**Faculty: Engineering**

The synthesis of new palm based polyol esters as the biodegradable base stock for lubricant production was conducted via chemical transesterification of palm based methyl esters with trimethylolpropane, 2-ethyl-2-(hydroxymethyl)-1,3-propanediol (TMP). Both palm oil (POME) and palm kernel methyl esters (PKOME) were used as the starting materials and sodium methoxide as the catalyst. The reactions were carried out under different temperatures (80 to 140°C) and vacuum pressures (0.1 to 500 mbar). Palm based TMP esters containing 98% w/w triesters was successfully synthesized in 45 minutes under 10 mbar vacuum, T=120°C, and 3.9:1 molar ratio of POME to TMP. While the effect of methyl esters to TMP ratio was minimal, the optimum molar ratio was found at 3.5:1 and 3.8:1 in palm kernel and palm oil TMP ester synthesis respectively. The amount of catalyst required was less than 1.0% w/w of the total mass of reactants. The optimal reaction conditions were: temperature, 130°C for POME and 120°C for PKOME; vacuum, 20 mbar; catalyst, sodium methoxide at 0.7% (w/w); POME:TMP, 3.8:1; PKOME:TMP, 3.5:1; duration, 1 hour. Analysis of the reaction products was performed using GC with a

high temperature capillary column, SGE HT5 operated at a temperature gradient of 6°C/min starting from 80°C to 340°C. Before injection, the sample was derivatized with N,O-Bis(trimethylsilyl)trifluoroacetamide (BSTFA) in ethyl acetate at 40°C for at least 10 min. This procedure provided a complete separation of the reaction products: TMP, palm based methyl esters, monoesters, diesters and triesters.

The kinetics study on transesterification of palm oil-based methyl esters with TMP established that the reactions occurred via three stepwise and reversible elementary reactions. The reversible reactions were suppressed by applying large excess of methyl esters and continual withdrawal of methanol via vacuum. The optimum ratios for  $k_2/k_1$  and  $k_3/k_1$  in palm oil TMP esters synthesis ranged from 0.70-0.80 and 0.21-0.25 respectively. For palm kernel TMP ester synthesis, the ratios for  $k_2/k_1$  and  $k_3/k_1$  were between 0.60-0.70 and 0.12-0.15. The activation energies of the reactions ranged from 17.2 to 33.9 kcal/mol. The lubrication properties of palm oil-based TMP esters indicated good potential as base stock in biodegradable lubricant formulation. Despite its high pour points, other lubrication properties such as viscosity, VI, wear and friction properties are comparable to commercial hydraulic fluids. The pour point (PP) problem associated with the saturation level in palm oil was resolved, as the PP was successfully improved to -32°C in high oleic palm based TMP esters. However, lowering the PP has negative effect on oxidative stability as well as wear and friction. With proper additives, it is believed that the new formulated high oleic palm oil TMP ester will offer a wide variety of applications: hydraulic fluids, fire resistant fluids, metalworking fluids, and general lubricating oils. Its unique chemistry offers excellent oxidative and thermal stability, superior low temperature behaviour, and biodegradability.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia sebagai memenuhi keperluan untuk ijazah Doktor Falsafah

**SINTESIS ESTER TRIMETILPROPANA MINYAK SAWIT DAN POTENSI  
PENGUNAAN SEBAGAI BAHAN ASAS MINYAK PELINCIR**

**Oleh**

**ROBI'AH BINTI YUNUS**

**October 2003**

**Pengerusi: Profesor Madya Fakhru'l-Razi Ahmadun, Ph.D.**

**Fakulti: Kejuruteraan**

Sintesis ester poliol minyak sawit sebagai bahan asas dalam penghasilan minyak pelincir biodegradasi dijalankan melalui proses transesterifikasi kimia metil ester minyak sawit dengan trimetilolpropana, 2-etil-2-(hidroksimetil)-1,3-propanadiol (TMP). Metil ester dari minyak kelapa sawit (POME) dan minyak isirong kelapa sawit (PKOME) digunakan sebagai bahan mentah dan sodium metoksida sebagai pemangkin. Tindakbalas dijalankan pada suhu 80 ke 140°C dan tekanan vakum, 0.1 ke 500 mbar. Ester TMP minyak sawit yang mengandungi 98% w/w triester telah berjaya disintesis dalam masa 45 minit pada tekanan 10 mbar, suhu 120°C dan nisbah mol POME:TMP, 3.9:1. Walaupun kesan nisbah mol POME (PKOME):TMP keatas tindakbalas adalah minima, nisbah optima adalah 3.5:1 dan 3.8:1 bagi sintesis ester TMP minyak sawit dan isirong minyak sawit. Jumlah pemangkin yang diperlukan adalah kurang dari 1% dari jumlah jisim bahan tindakbalas. Keadaan tindakbalas optima adalah: suhu, 130°C bagi POME and 120°C bagi PKOME; tekanan: 20 mbar; pemangkin: sodium metoksida pada 0.7% (w/w); POME: TMP, 3.8:1; PKOME: TMP, 3.5:1; masa, 1 jam. Analisis hasil tindakbalas dibuat

menggunakan GC dengan turus kapilari bersuhu tinggi, SGE HT5 pada suhu berkala  $6^{\circ}\text{C}/\text{min}$  dari  $80^{\circ}\text{C}$  ke  $340^{\circ}\text{C}$ . Sebelum disuntik, sampel ditindakabalaskan dengan N,O-Bis(trimetilsilil) trifluoroacetamida (BSTFA) dalam etil acetat pada suhu  $40^{\circ}\text{C}$  selama 10 min. Kaedah ini membolehkan analisa kuantitatif kerana pemisahan lengkap hasil tindakabalas seperti: TMP, metil ester, monoester, diester dan triester.

Kajian kinetik keatas transesterifikasi metil ester minyak sawit dengan TMP menunjukkan tindakabalas berlaku secara turutan melibatkan tiga tindakbalas asas berbalik. Tindakbalas berbalik dikurangkan dengan menggunakan metil ester lebihan dan penyingkiran berterusan metanol melalui vakum. Nisbah optimum pekali tindakbalas  $k_2/k_1$  and  $k_3/k_1$  dalam sintesis ester TMP minyak sawit berada pada julat 0.70-0.80 dan 0.21-0.25. Bagi sintesis ester TMP minyak isirong sawit, nisbah  $k_2/k_1$  dan  $k_3/k_1$  adalah diantara 0.60-0.70 dan 0.12-0.15. Tenaga keaktifan tindakabalas bagi sintesis tersebut berada diantara 17.2 to 33.9 kcal/mol. Ujian pelinciran keatas ester TMP minyak sawit menunjukkan potensi tinggi minyak tersebut sebagai bahan asas dalam formulasi minyak pelincir biodegradasi. Walaupun takat tuang (PP) tinggi, kelikatan, indeks kelikatan, ciri haus dan geseran adalah setara dengan minyak hidralik yang ada dipasaran. Masalah PP yang dikaitkan dengan tahap tepu minyak sawit telah dapat diselesaikan dengan penemuan baru, ester TMP minyak sawit oleik tinggi dimana PP dapat dikurangkan ke  $-32^{\circ}\text{C}$ . Walaubagaimanapun, pengurangan PP menimbulkan kesan negatif kepada kestabilan oksida dan ciri haus serta geseran. Dengan penggunaan bahan tambah tertentu, minyak sawit oleik tinggi dipercayai dapat digunakan dalam pelbagai kegunaan: bendalir hidralik, bendalir logamkerja, dan minyak pelincir am. Ciri kimianya yang unik menawarkan kestabilan terma dan oksida yang tinggi, sifat suhu rendah yang baik dan biodegradasi.

## ACKNOWLEDGEMENTS

I would like to extend my deepest gratitude and appreciation to the supervisory committee; Chairman, Associate Professor Dr. Fakhru'l-Razi Ahmadun; Committee Members, Dr. Ooi Tian Lye, Associate Professor Dr. Sunny M. Iyuke, and Associate Professor Dr. Azni Idris for providing invaluable advice, untiring assistance, encouragement, motivation and support that enabled me to accomplish the PhD program smoothly and efficiently. My special thanks and appreciation to Dr. Salmiah Ahmad, Head of Advanced Oleochemical Technology Centre (AOTC), Malaysian Palm Oil Board for allowing me to carry out the experimental work at the centre and their continuing support and assistance.

I am also grateful to the staff members of AOTC laboratories (ANI and Analytical), Dr. Hazimah, Dr. Yong, Asma, Rosmah, Supiah, Maznee, Noreen, Bahriah, En. Aziz, Akhir, Khomsaton, and others for their kind assistance throughout the course of the study. Also special thanks to all my colleagues at the Department of Chemical and Environmental Engineering, Siti Zubaidah, Hazmin, Dr. Dayang, Dr. Amran, Faizah, Ghani, Halim, Suriani, Rozita Shafreeza, Intan, Rogayah, Maslinda, Siti and others for their constant support and encouragement. Grateful acknowledges are extended to the staff members of Faculty of Engineering for their sincere help and cooperation.

I am also grateful to the Government of Malaysia for providing financial support under the IRPA grant (Vot 54103) and Universiti Putra Malaysia for the short-term research grant (Vot 50612).



My heartfelt and sincere appreciation goes to my children; Mohd. Muzammil, Mohd. Mudzakhir, Nazratul Fareha, Aina Nadhirah, my mother, Khadijah Awang and other relatives and friends who always encouraged and supported me during the study period. Last but not least, my special thanks to my husband, Salahuddin Abdul Manap, for his love, constant encouragement, sacrifices, patience, and understanding that enable me to finish the study smoothly and timely.

I certify that an examination committee has met on 2<sup>nd</sup> October 2003 to conduct the final examination of Robi'ah binti Yunus on her Doctor of Philosophy thesis entitled "Synthesis of Palm-based Trimethylolpropane Esters and Their Potential Use as Lubricant Base Stock" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The committee recommended that the candidate be awarded the relevant degree. The Committee Members for the candidate are as follows:

**Ibrahim Omer Mohamed, Ph.D.**

Lecturer  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Fakhru'l-Razi Ahmadun, Ph.D.**

Associate Professor  
Faculty of Engineering, Universiti Putra Malaysia  
(Member)

**Ooi Tian Lye, Ph.D.**

Principal Research Officer  
Advanced Oleochemical Technology Center  
Malaysian Palm Oil Board (MPOB)  
(Member)

**Sunny E. Iyuke, Ph.D.**

Associate Professor  
Faculty of Engineering, Universiti Putra Malaysia  
(Member)

**Azni Idris, Ph.D.**

Associate Professor  
Faculty of Engineering, Universiti Putra Malaysia  
(Member)

**K. B. Ramachandran, Ph.D.**

Professor  
Faculty of Engineering,  
Universiti Malaya  
(Independent Examiner)



**GULAM RUSUL RAHMAT ALI, Ph.D.**

Professor/Deputy Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date: 01 DEC 2003

This thesis submitted to the Senate of Universiti Putra Malaysia has been accepted as fulfillment of the requirements for the degree of **Doctor of Philosophy**. The members of the Supervisory Committee are as follows:

**Fakhru'l-Razi Ahmadun, Ph.D.**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Chairman)

**Ooi Tian Lye, Ph.D.**

Principal Research Officer  
Advanced Oleochemical Technology Center  
Malaysian Palm Oil Board (MPOB)  
(Member)

**Sunny E. Iyuke, Ph.D.**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)

**Azni Idris, Ph.D.**

Associate Professor  
Faculty of Engineering  
Universiti Putra Malaysia  
(Member)



**AINI IDERIS, Ph.D.**

Professor/Dean  
School of Graduate Studies  
Universiti Putra Malaysia

Date : 8 JAN 2024

## DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at Universiti Putra Malaysia or other institutions.



ROBIAH BINTI YUNUS

Date: 28 Nov . 2003

## TABLE OF CONTENTS

	Page
DEDICATION	2
ABSTRACT	3
ABSTRAK	5
ACKNOWLEDGEMENTS	7
APPROVAL	9
DECLARATION FORM	11
TABLE OF CONTENTS	12
LIST OF TABLES	15
LIST OF FIGURES	17
LIST OF ABBREVIATIONS	21
 <b>CHAPTER</b>	
 1. INTRODUCTION	23
1.1 Background	23
1.2 Objectives and Scopes of Work	30
1.3 Thesis Outline	31
 2. LITERATURE REVIEW	33
2.1 Introduction	33
2.2 Lubricants and the Environment	33
2.3 Historical Development	37
2.4 Lubricant Principles	39
2.5 Classification of Lubricants	40
2.5.1 Mineral Oil Lubricants	41
2.5.2 Synthetic Lubricants	43
2.5.3 Vegetable Oil-Based Lubricants	45
2.5.4 Vegetable Oil-Based Synthetic Esters	49
2.6 Lubricants Performance Requirement	55
2.7 Lubricants Market and Price	57
2.8 Synthesis of Vegetable Oil-Based Esters	60
2.8.1 Chemical Synthesis	63
2.8.2 Enzymatic Synthesis	67
2.9 Reaction Kinetics	74
2.9.1 Kinetics of Transesterification of Palm-Based Methyl Esters with Trimethylolpropane Determination of Rate Equation from	80
2.9.2 Determination of Rate of Equations from Laboratory Data	85
2.10 Testing and Analysis	94
2.10.1 Chemical and Physical Properties	95
2.10.2 Mechanical Properties	104
2.10.3 Engine Testing	107
2.10.4 Lubricant Additives	108
 3. DEVELOPMENT OF ANALYTICAL TECHNIQUE	111
3.1 Introduction	111
3.2 Materials and Methods	112
3.2.1 Materials	112

3.2.2	Standard Solutions	112
3.2.3	Validation	113
3.2.4	Fatty Acids Analysis	113
3.2.5	Thin Layer Chromatography (TLC)	114
3.2.6	High Pressure Liquid Chromatography (HPLC)	115
3.2.7	Gas Chromatography (GC)	115
3.2.8	Fourier Transform Infrared Refractometer (FTIR)	115
3.3	Results and Discussions	116
3.3.1	Fatty Acids Analysis	116
3.3.2	TLC	116
3.3.3	HPLC	117
3.3.4	GC	119
3.3.5	FTIR	125
3.4	Conclusions	127
4.	SYNTHESIS OF PALM-BASED POLYOL ESTERS	129
4.1	Introduction	129
4.2	Materials	131
4.3	Experimental Procedures	131
4.3.1	Synthesis of Palm-based Polyol Esters	131
4.3.2	Sampling	134
4.3.3	Removal of Catalyst	135
4.3.4	Removal of Unreacted Methyl Ester	136
4.4	Results and Discussions	137
4.4.1	Reaction Mechanism	137
4.4.2	Effect of Fatty Acids Composition	138
4.4.3	Effect of Temperature	140
4.4.4	Effect of Pressure	143
4.4.5	Effect of Reactants Molar Ratio	148
4.4.6	Effect of Catalyst	150
4.5	Conclusions	153
5.	TRANSESTERIFICATION KINETICS OF PALM-BASED METHYL ESTERS WITH TRIMETHYLOLPROPANE	155
5.1	Introduction	155
5.2	Isothermal Reactions	157
5.3	Model Development	159
5.3.1	Reaction Kinetics	164
5.3.2	Determination of Reaction Rate Constants	165
5.3.2.1	Rate Constant, $k_1$	166
5.3.2.2	Rate Constant, $k_2$	168
5.3.2.3	Rate Constant, $k_3$	172
5.3.3	Discussions on Rate Constants	175
5.3.4	Activation Energy, $E_a$	178
5.3.5	Model Verification	180
5.4	Conclusions	185

<b>6. LUBRICATION CHARACTERISTICS OF PALM-BASED SYNTHETIC LUBRICANTS</b>	<b>187</b>
6.1 Introduction	187
6.2 Experimental Procedures	188
6.2.1 Pour Point	188
6.2.2 Viscosity and Viscosity Index	189
6.2.3 Wear and Friction	189
6.2.4 Oxidative Stability	190
6.2.5 Differential Scanning Calorimeter (DSC)	190
6.3 Results and Discussions	191
6.3.1 Pour Point	191
6.3.2 Kinematic Viscosity and Viscosity Index	194
6.3.3 Wear and Friction Properties	196
6.3.4 Oxidative and Thermal Stability	206
6.3.4.1 Penn State Micro-oxidation Thin-Film Test	207
6.3.4.2 Differential Scanning Calorimeter (DSC)	208
6.4 Conclusions	213
<b>7. HIGH OLEIC PALM-BASED LUBRICANTS</b>	<b>215</b>
7.1 Introduction	215
7.2 Synthesis of High Oleic Palm-Based Lubricants	215
7.2.1 Materials and Methods	217
7.2.2 Results and Discussion	219
7.3 Performance Testing	222
7.3.1 Iodine Value	222
7.3.2 Saponification Value	222
7.3.3 Moisture Content	223
7.3.4 Pour Points	223
7.3.5 Viscosity and Viscosity Index	226
7.3.6 Wear and Friction Properties	226
7.3.7 Oxidative Stability	231
7.3.8 Other Chemical Properties	235
7.4 Conclusions	240
<b>8. CONCLUSIONS AND RECOMMENDATIONS</b>	<b>241</b>
8.1 Conclusions	241
8.2 Recommendations for Future Work	244
<b>REFERENCES</b>	<b>245</b>
<b>APPENDICES</b>	<b>258</b>
A. GC and TLC Chromatograms	
B. Photographs of Samples	
C. Raw Data	
<b>BIODATA OF THE AUTHOR</b>	<b>287</b>

## LIST OF TABLES

Table		Page
2.1	Allocation of lubricants within the water hazard classification	34
2.2	Acute toxicity of petroleum additives	35
2.3	Granting regulations for the environmental label “Blue Angle”	36
2.4	Modern milestones in biodegradable lubricating fluids	38
2.5	Typical inspection properties of hydro finished HVI Stocks	42
2.6	Typical classes of synthetic materials	43
2.7	Physical characteristics of typical synthetic fluids	44
2.8	Fatty acid percentage compositions for common vegetable oils	45a
2.9	Lubricant demand and supply by region – 1990 estimates	58
2.10	Relative costs of synthetic oils compared to mineral oil	59
3.1	Average fatty acids compositions of palm oil based (POME) and palm kernel based (PKOME) methyl esters	116
3.2	Average retention times for components obtained from reaction between methyl palmitate and methyl laurate with trimethylolpropane	123
4.1	Effect of fatty acids composition (% w/w) on final product at various temperatures	138
4.2	Effect of temperature on palm oil trimethylolpropane ester synthesis at 130°C (POME: TMP 3.9:1; catalyst 0.9% w/w; 0.2mbar, 4 h)	142
5.1	Rate constant, $k_1$ for reaction between TMP and palm-based methyl ester	164
5.2	Effects of $t_{max}$ and $k_2$ on calculated [ME] of Palm oil TMP esters at 70°C	167
5.3	Variation of rate constant, $k_3$ with $t_{max}$ of [DE] in synthesis of palm oil TMP esters at 90°C	170
5.4	Average reaction rate constants at different temperatures in synthesis of palm oil and palm kernel TMP esters	174



5.5	Activation energies for transesterification of TMP, monoesters (ME) and diesters (DE) with palm oil and palm kernel oil methyl esters	176
6.1	Composition and pour points of selected palm-based polyol esters	192
6.2	Kinematic viscosity and viscosity index of selected palm-based polyol esters	194
6.3	Chemical composition of palm-based polyol ester test fluids	196
6.4	Wear and friction properties of palm-based polyol esters	197
7.1	Fatty acid composition of distilled palm oil methyl esters	216
7.2	Product Composition of High Oleic Palm Oil TMP Esters at Various Temperatures	221
7.3	Pour points of different grades of high oleic palm oil TMP esters	224
7.4	Characteristics of different grades of high oleic palm oil TMP esters	225
7.5	Wear scar diameter (WSD) of lubricating oils at 40 kg load	227
7.6	Wear scar diameter (WSD) of lubricating oils at 15 kg load	227
7.7	Chemical and corrosion properties of palm-based lubricants	236

## LIST OF FIGURES

Figure		Page
2.1	Biodegradability of different base oils	34
2.2	Stribeck curve	40
3.1	TLC plates showing the elution of partial polyol esters at two different solvent ratios (a) n-heptane:ethyl acetate, 83:17, (b) n-heptane:ethyl acetate, 95:5.	117
3.2	HPLC Chromatogram of palm oil based polyol esters derived from reaction between palm oil methyl esters (POME) and trimethylolpropane (TMP) <sup>a</sup> (molar ratio of TMP and POME, 1:3.9; sodium methoxide, 0.9%, 140°C, 0.3 mbar, 5 h)	118
3.3	GC chromatogram of palm oil based polyol esters derived from reaction between palm oil-based methyl esters and trimethylolpropane (TMP) (a) palm kernel oil methyl esters (PKOME) (b) palm oil methyl esters (POME) Physical characteristics of typical synthetic fluids	122
3.4	GC chromatogram showing the position of TE48 and TE54 relative to TG30	124
3.5	GC separation showing the progress of reaction between palm kernel oil methyl esters and trimethylolpropane	126
3.6	FTIR Spectrums (a) TMP, (b) Palm Oil Methyl Ester and (c) Palm Oil-Based TMP Esters	128
4.1	Experimental setup for synthesis of palm-based TMP ester	132
4.2	Effect of Temperature on Transesterification of Palm Kernel Oil Methyl Esters with Trimethylolpropane (PKOME:TMP, 3.9:1; catalyst 0.9%w/w; 0.2mbar, 4 h)	140
4.3	Effect of temperature on transesterification of palm oil methyl esters with trimethylolpropane (PKOME:TMP, 3.9:1; catalyst 0.9% w/w; 20 mbar, 4 h)	141
4.4	Effect of temperature on transesterification of palm oil methyl esters with trimethylolpropane (PKOME:TMP 3.9:1; catalyst 0.9% w/w; 10 mbar, 4 h)	142
4.5	Effects of temperature and time on triesters composition in	142

synthesis of palm kernel TMP Esters (POME/TMP, 3.9:1, catalyst 0.9 % wt. , 10 mbar)

4.6	Effect of vacuum on transesterification of palm oil methyl esters with TMP Molar ratio of POME: TMP was 3.9:1, catalyst 0.9 % wt., 130°C	144
4.7	Effect of vacuum on product composition in transesterification of PKOME with TMP (PKOME: TMP was 3.9:1, catalyst 0.9 % wt., 130°C)	146
4.8	Time courses of palm kernel TMP ester synthesis at various vacuum pressures (PKOME: TMP, 3.9:1; catalyst 0.9 % wt.; 130°C)	147
4.9	Effects of molar ratio on transesterification of PKOME with TMP (a) TE composition (% w/w) based on total weight including PKOME (b) % w/w without PKOME	149
4.10	Effects of molar ratio on transesterification of palm oil methyl esters with trimethylolpropane. (a) % w/w based on total weight including POME (b) TE composition (% w/w) without POME	150
4.11	Effect of catalysts on transesterification of palm kernel methyl esters with trimethylolpropane, T=130°C, 10 mbar and 3.8:1 ratio	151
4.12	Effect of catalysts on transesterification of palm oil methyl esters with trimethylolpropane, T=130°C, 10 mbar and 3.8:1 ratio	152
5.1	Comparison between calculated and experimental values of [TMP] in transesterification of palm oil methyl esters with TMP at 80°C, $k_1=0.1877$	157
5.2	Effect of temperature and time on composition of triesters (TE) in transesterification of palm oil methyl esters with TMP	159
5.3	Effect of temperature and time on composition of triesters in transesterification of palm kernel methyl esters with TMP	160
5.4	Second order kinetics model for transesterification of palm oil methyl esters with TMP, (a) palm oil (b) palm kernel oil, Slope = $(C_{BO} - C_{AO})k_1$ .	164
5.5	Pseudo-first kinetics model for transesterification of palm-based methyl ester with TMP (a) palm kernel oil (b) palm oil, Slope = $k_1$	165

5.6	Effects of $k_2$ on $[ME]_{calc}$ (%w/w) in Palm oil based TMP esters synthesis and comparison with $[ME]_{exp}$ at $k_1=0.0368$ , $70^\circ C$ .	167
5.7	Effects of $k_2$ on calculated $[ME]$ (%w/w) of Palm kernel TMP esters and comparison with experimental $[ME]$ at $k_1=0.1538$ at $80^\circ C$	168
5.8	Effects of $k_3$ on calculated DE in synthesis of palm oil TMP esters at $90^\circ C$ and $k_1=0.237$ ; $k_2=0.262$	169
5.9	Effects of $k_2$ on calculated DE in synthesis of palm oil TMP esters at $k_1=0.5417$ ; $k_3=0.0942$	171
5.10	Effect of $k_3$ at different $t_{max}$ on calculated DE (wt%) in palm kernel TMP ester synthesis at $80^\circ C$ and $k_1=0.1538$ and $k_2 = 0.0978$	171
5.11	Effect of $k_2$ at different $t_{max}$ on calculated DE (wt%) in palm kernel TMP ester synthesis at $80^\circ C$ and $k_1=0.1538$ and $k_3 = 0.0218$	172
5.12	Arrhenius Plot showing the temperature dependency of the reaction rate constants (a) palm kernel TMP ester (b) palm oil TMP ester	173
5.13	Comparison between calculated and experimental values of $[TMP]$ in transesterification of palm oil methyl esters with TMP at $80^\circ C$ , $k_1=0.1877$	176
5.14	Comparison between calculated and experimental values of $[DE]$ in transesterification of palm oil methyl esters with TMP at $80^\circ C$	179
5.15	Comparison between calculated and experimental values of $[ME]$ in transesterification of palm oil methyl esters with TMP at $80^\circ C$	180
6.1	Four Ball tester	190
6.2	Penn State Thin-Film Micro-oxidation unit	191
6.3	Kinematic viscosities and viscosity stability index of various vegetable oils and TMP esters	195
6.4	Wear comparisons for different palm oil polyol esters	197
6.5	Friction coefficients for palm oil TMP esters	198
6.6	Wear comparison for different palm kernel oil polyol esters	199

6.7	Friction coefficients for palm kernel TMP esters	202
6.8	Friction coefficients for palm kernel TMP esters	200
6.9	Friction coefficients for Palm kernel TMP esters	203
6.10	Average coefficient of friction for palm-based TMP esters	205
6.11	Thin-film micro-oxidation test results	206
6.12	DSC-TGA determination of oxidation onset temperature of palm kernel and palm oil TMP esters in air	210
6.13	DSC-TGA spectrum for thermal decomposition of palm kernel and palm oil TMP esters in nitrogen	211
6.14	Rate of weight loss for palm kernel TMP esters under nitrogen and air	212
7.1	Product distribution curves for the transesterification of palm oil-based methyl esters with TMP at 150°C and 0.3 mbar: Monoesters (ME), diesters (DE), triesters (TE), trimethylolpropane (TMP) and high oleic palm oil methyl esters (POME)	219
7.2	The effect of temperature and time on the composition of triesters (TE) in the synthesis of high oleic palm oil-based polyol esters: Molar ratio of POME/TMP was 3.9:1, catalyst 0.9 % wt.	220
7.3	Oxidation stability test results using DSC	231
7.4	Rotary bomb oxidation stability test (RBOT) results	233

## LIST OF ABBREVIATIONS/NOTATION/GLOSSARY OF TERMS

### *Abbreviations*

DE	Diesters
DG	Diglycerides
FTIR	Fourier transform infrared refractometry
GC	Gas chromatography
HPLC	High pressure liquid chromatography
M	Methanol
MG	Monoglycerides
ME	Monoesters
PA	Polyol
PE	Polyol ester
PKOME	Palm kernel oil methyl esters
POME	Palm oil methyl esters
POTE	High oleic palm oil TMP esters
PKOTE	Palm kernel oil TMP esters
PPOTE	Palm oil TMP esters
TE	Triesters
TG	Triglycerides
TMP	Trimethylolpropane
TLC	Thin layer chromatography

### *Nomenclatures*

$C_A, C_B, C_C, \text{ and } C_D$	Concentrations of components A, B, C and D ( $\text{mol/dm}^3$ )
$C$	Average concentration of an adsorbed species ( $\text{mol/dm}^3$ )
$C_m$	Concentration corresponding to a complete formation of monomolecular layer on the catalyst surface ( $\text{mol/dm}^3$ )
$C_v$	Concentration of vacant sites ( $\text{mol/dm}^3$ )
[POME]	Composition of POME (wt %)
[ME]	Composition of ME (wt %)
[DE]	Composition of DE (wt %)
[TE]	Composition of TE (wt %)
$E$	Activation energy (cal/mol)
$K$	Equilibrium constant (dimensionless)
$K_A$	Adsorption equilibrium constant (dimensionless)
$k_1, k_2, k_3$	Reaction rate constants for reactions 1, 2, and 3 ( $\text{wt}^{-1}\text{min}^{-1}$ )
$k_1', k_2', k_3'$	Reaction rate constants for reverse reactions 1, 2, and 3 ( $\text{wt}^{-1}\text{min}^{-1}$ )
$k_a$	Rate constant for adsorption
$k_a'$	Rate constant for desorption
$R_1$	$\{[TMP_o]k_1k_2\}/R_2R_3R_4$
$R_2$	$(k_2-k_3)$
$R_3$	$(k_1-k_3)$
$R_4$	$(k_1-k_2)$
$\alpha$	$k_2/k_1$

$\beta$	$k_3/k_1$
$\delta$	$k_1/(k_1-k_2)$
$\nu$	Kinematic viscosity, mm <sup>2</sup> /s (cSt)
$\mu$	Dynamic viscosity, mPa.s (cP)
$\rho$	Density (g/ml)
Subscript <sub>A, B, C, D</sub>	Reacting components A, B, C and D
Subscript <sub>i, j</sub>	ith or jth component
Subscript <sub>o</sub>	Initial condition
Superscript <sup><math>\alpha, \beta, \gamma</math>, and <math>\delta</math></sup>	Orders of reaction

## CHAPTER 1

### INTRODUCTION

#### 1.1 Background

Biodegradable lubricants in the form of animal and vegetable fats and oils have been in use since ancient history. However, in the second half of the 20<sup>th</sup> century these natural lubricants are predominantly replaced by mineral-based lubricants due to its cost and performance considerations (Dowson, 1997). Despite its inherent limitations, natural fats and oils continued to play an important role in lubricant formulation. According to Formo (1982), about 10,000 tonnes (20 millions pounds) of fats and oils were used for lubricants production in 1962 and increased to 100,000 tonnes in 1976. The US Department of Agriculture has estimated about 54,000 tonnes (108 million pounds) of vegetable oils was used in lubricant formulations in 1993, out of 70 million tonnes of vegetable oils currently produced worldwide (Margaroni, 1999). This figure represents approximately 0.5% of total lubricants supplied to the US market. (Honory and Boeckendstedt, 1998)

Today, most of the lubricants and functional fluids are derived exclusively from petrochemical or mineral bases. They account for 85-90 % of the total world lubricants. Whilst, less than 15% of the world lubricants are synthetic-based, the synthetic-based lubricants offer high performance oil with superior lubricity, higher thermal stability, excellent oxidative stability, lower volatility, and hence fewer oil change requirement (Moore *et al*, 2003; Shanley and Butcher, 1999). Due to its poor oxidative stability, vegetable oil-based lubricants account for only 1% of total world lubricants. Adding additives such as antioxidant and pour point depressant enhances the properties of these biodegradable lubricants.



The awareness of preserving the environment has inspired research and development in environmental friendly products such as biodegradable lubricants. Lubricants are one of many hazardous contaminants of our environment, almost 90% are mineral-based and most of the used oils are not regenerated. It is reported that every year million tonnes of engine, industrial and hydraulic oils leak into the ground, waterways or are disposed off into the environment. It was calculated that up to 600,000 tons of oil a year disappear uncontrolled in the European Community (EC) alone (Wilson, 1998). According to the US Navy statistics, the total oil spilled in the US coasts is increasing alarmingly, from 17,370 gallons in 1990 to 66,404 in 1997 and up to 181,453 gallons in 1998 (Johnson, 1999).

The modern developments in high-performance biodegradable lubricants began only in the 1970's. The first biodegradable lubricant was two-stroke oil based on synthetic esters, which was commercially available in 1975. It was developed in response to the increasing environmental concern over the use of petroleum-based lubricants in environmentally sensitive areas and in once-through applications. Many large corporations such as Mobil Oil Co., BP, Castrol and Shell have formulated range of biodegradable products with specific applications. These products are available commercially and conformed to various categories of biodegradable lubricants classifications such as German's "Blue Angel" Eco-label (Hery and Battersby, 1998; Kiovsky *et al.*, 1994).

The most critical areas requiring biodegradable lubricants are the "total loss" or "once through" materials such as chain saw lubricants, two-cycle-engine oils, and hydraulics fluids (Kiovsky *et al.*, 1994). Due to the higher risks in entering soil and